

# 700 $\mu\text{m}$ Uv Net



	Test Standard	Lado Side	Media Middle	Promedio Average			
Espeor Thickness	DIN 53.353 mm	0.77	0.74	0.75			
Peso metro cuadrado: Weight square meter	DIN EN ISO 2286-2 gsm	903	871	887			
Andho de bobina: Width roll:	cm			<b>250</b>			
Metros bobina: Roll meters:	mts			<b>20</b>			
Peso bobina: Weight roll:	Kg			38			
Resistencia a la tracción: Tensile Strength:	DIN 53.354 N/5cm	MD	CD	MD	CD	MD	CD
		783	728	745	743	764	735
Extensión a la rotura: Extension at Break:	DIN 53.364 %	31	32	32	34	31	33
Resistencia al desgarro: Tear Strength:	DIN 53.363 N	251	339	251	307	251	323
Adhesion: Haftung:	DIN 53.357 N/5 cm	Side A	71	73	72.5		
		Side B	67	75	71		
Rango de temperature: Temperature resistance:	- 20 °C + 70 °C						
Color / Colour	Transparente / Transparent						
Grabado/ Emboss	Ninguno / None						
Conductividad térmica: Thermal conductivity:	W/m.k.			0.16			
Comportamiento al fuego: Fire behaviour:	Autoextinguible						

NORMAS DE LIMPIEZA: Limpiar con un trapo húmedo y enjabonado. Usar sólo jabón neutro. Enjuagar con agua limpia. No usar disolventes, blanqueadores, detergentes químicos o sprays abrillantadores.  
 CLEANING RULES: Clean with damp soapy cloth and rinse well with clean water. Do not use solvents, bleaches, synthetic detergents, polishes or aerosol spray.



Esta información está basada en los resultados de experiencias y test , y suministrada como guía.  
 This information is based on results from experience and tests and given to be used as guideline

15.09.2022